


Technical Data Sheet

Ref: VCPPL/QA/TDS/01 Rev : 1.1 Date : 23.12.2024

Product Category : 4 mm -0.50 Skin Thickness-AA 3105 Alloy- 7 Star - FR-A2



Sr. No.	Test Parameters	Test Method	Specifications	Result
A	Physical Property of Aluminium Composite Panel			
1	Thickness of Panel ,mm	Measured	4 (± 0.20)	4.03
2	Panel Weight, [Kg/m2]	Measured	8.20 (±5%)	8.24
3	Specific Gravity of Panel	ASTM D 1505	2.05(±5%)	2.04

✉ info@vivaacp.com

🌐 www.vivaacp.com

☎ 1800 313 3770 (Toll Free)

📍 **Registered Office :** A-601, Times Square, Marol Naka, Andheri (E), Mumbai, India - 400 059

📍 **Factory Address :** Survey No. 85/8, 85/9, 85/10, 68/1, 70/14, Khattalwada, Manekpur Road, Tal - Umbergaon, Dist-Valsad, Station-Sanjan, Gujarat - 396120



B	Mechanical Properties of Aluminium Composite Panel			
1	Tensile Strength, Mpa	ASTM D 638	Min 45	48.3
2	Yield Strength, Mpa	ASTM D 638	Min 40	43.5
3	Elongation,%	ASTM D 638	≥5	7.1
4	Bending Strength, Mpa	ASTM C 393	Min. 100	110
5	Flexural Modulus, Mpa	ASTM C 393	≥20000	22854
6	Peel off Strength, N/mm	ASTM D 903	Min. 9	9.19
7	Shear Strength, MPa	ASTM C 393	Min. 22	23
8	Drum Peel Strength, N-mm/mm	ASTM D 1781	Min. 100	112
C	Mechanical Properties of Aluminium Coil/Skin			
1	Thickness of Aluminium Coil, mm	Measured	0.50±0.03	0.505
2	Aluminium Alloy	ASTM B 209	AA 3105, H24	AA 3105, H24
3	Tensile Strength, [N/mm ²]	ASTM E8	Min 150	175
4	0.2% Proof Stress, [N/mm ²]	ASTM E8	Min 125	161
5	Elongation,%	ASTM E8	>2	4.45
6	Modulus of Elasticity, Mpa	ASTM E8	>68000	71050
D	Thermal Properties of Aluminium Composite Panel			
1	Thermal Resistance (R), (m ² K/W)	ASTM C 518	-	0.336
2	Coefficient of Thermal Conductivity(U)	ASTM C 518	-	2.98
3	Temperature Resistance (°C)	By Measurement	-50 to +80	-50 to +80
4	Heat Deflection Temperature (°C)	ISO 75-2	-	90
5	Linear Thermal Expansion(μm/m-°C)	ASTM D 696	-	152

✉ info@vivaacp.com

🌐 www.vivaacp.com

☎ 1800 313 3770 (Toll Free)

📍 **Registered Office :** A-601, Times Square, Marol Naka, Andheri (E), Mumbai, India - 400 059

📍 **Factory Address :** Survey No. 85/8, 85/9, 85/10, 68/1, 70/14, Khattalwada, Manekpur Road, Tal - Umbergaon, Dist-Valsad, Station-Sanjan, Gujarat - 396120

E	Fire Performance of Aluminium Composite Panel			
1	Reaction to Fire	EN 13501-1	A2- s1,d0	A2- s1,d0 (TBW0300742)
2	Surface burning test	ASTM E 84	Flame Spread Index & Smoke Developed Index	FSI-15 & SDI-115 (TBW0300990)
3	Ignition temperature of core	ASTM D1929	Self-Ignition Temperature & Flash Ignition Temperature	SIT- 509°C & FIT -506°C (TBW0300990)
4	Ignition temperature of material	ASTM D1929	Self-Ignition Temperature & Flash Ignition Temperature	SIT- 475°C & FIT – 468°C (TBW0300990)
5	Reaction to fire for Building	NFPA 285	-	Passed (TBW0300914)
6	Calorific Value (Gross Heat Of Combustion)	EN ISO-1716	PCS≤3MJ/Kg	0.8 MJ/Kg (UC021-1)
7	Certificate of Conformity	EN 13501-1 , ASTM E 84, ASTM D1929 -	A2- s1,d0	Pass (ESL-24-11641)
8	Certificate of Conformity	NFPA 285		Pass (ESL-24-11642)
F	Coating Properties Top coil of Aluminum Composite Panel**			
1	Dry Film Thickness (Coating), [μm] 3-coat Primer: 5-7μm Top Coat: 18-20μm Clear Coat: 10μm	ASTM D 7091	Min. 30μm	31.9
2	Dry Film Thickness (Coating), [μm] 2-coat Primer: 5-7μm Top Coat: 18-20μm	ASTM D 7091	Min. 24μm	26
3	Coating Type	FTIR Method	PVDF, KYNAR 500/FEVE	PVDF(KYNAR 500)
4	Specular Gloss, %	ASTM D 523	STD ±5	28.3
5	Abrasion Resistance	ASTM D 968	≥2L/ μm	>2
6	Color Retention (4000 hrs.)	ASTM D 2244	7 Unit (Max.)	0.89
7	Chalk Resistance (4000 hrs.)	ASTM D 4214	Max. Rating 8	No Chalking
8	Salt Spray (4000 hrs.)	AAMA 2605 (ASTM G 85)	No Damage	No creepage
9	Humidity Resistance (4000 hrs.)	AAMA 2605 (ASTM D 2247)	No Damage	No Blisters
10	Cross Hatch (Adhesion Test) Dry @27°C Wet @38°C, 24 hrs Boiling @100°C, 20min	ASTM D 3359	No removal of film	No Adhesion Loss, Pass
11	Impact Resistance	AAMA 2605	No removal of film	65inch-Lbs, Pass
12	Pencil Hardness Test, [F-H]	ASTM D 3363	Min F	3H Pass
13	T-Bend Flexibility, [T]	ASTM D 4145	Max 2T	2T Pass

✉ info@vivaacp.com

🌐 www.vivaacp.com

☎ 1800 313 3770 (Toll Free)

📍 **Registered Office :** A-601, Times Square, Marol Naka, Andheri (E), Mumbai, India - 400 059

📍 **Factory Address :** Survey No. 85/8, 85/9, 85/10, 68/1, 70/14, Khattalwada, Manekpur Road, Tal - Umbergaon, Dist-Valsad, Station-Sanjan, Gujarat - 396120

GCoating Properties Bottomcoil of Aluminum Composite Panel**				
1	Dry Film Thickness (Coating), [μm]	ASTM D 7091	5-7μm	6
2	T-Bend Flexibility, [T]	ASTM D 4145	Max 2T	2T Pass
3	Solvent Resistance (MEK- Methyl Ethyl Ketone)	ASTM D 5402	>50 DR @ 1Kg Load	50DR, Pass
4	Cross Hatch (Adhesion Test)	AAMA 2605	No removal of film	No Adhesion Loss, Pass
5	Boiling Water Test @100°C, 20min	AAMA 2605	No removal of film	No Adhesion Loss, Pass
6	Traceability	Viva Standard	As per material	Pass
HChemical Test of Aluminum Composite Panel (Drop Test)				
1	1. Muriatic Acid(HCl) Resistance, 15 minutes spot test	AAMA 2605	No visible defects must be seen	No Change
	2. Mortar Resistance, 24 Hour Pat test			
	3. Nitric Acid (HNO ₃) Resistance, 30 minutes fume test			
	4. Detergent Resistance, 72 Hour Immerse test			
2	Alkali Solution (NaOH) Resistance	ASTM D 1308	No visible defects must be seen	No Change
	Acidic Solution (HCl) Resistance			
3	Solvent Resistance (MEK- Methyl Ethyl Ketone)	ASTM D 5402	>100 DR @ 1Kg Load	Resistant
IDimensioning Details				
	Parameter	Range	Unit	Standard Tolerance
1	Width	Std.1220, Can be customized till 1670mm.	mm	-/+2
2	Length	Std. 2440, 3050, 3660, Can be customized till 6000mm.	mm	-/+4
3	Squareness	-	mm	-/+2
4	Bow	-	%	-/+0.5
J	Scan the QR code below to follow the Installation Guidelines 			
Note * Specification limits as per ASTM and different international standards. ** Coating is compliant with AAMA 2605. *** Gloss varies from color to color and depends on paint type.. ****Customization is possible in Alloys, Paint type, Color,Size based on MOQ.				

✉ info@vivaacp.com

🌐 www.vivaacp.com

📞 1800 313 3770 (Toll Free)

📍 **Registered Office :** A-601, Times Square, Marol Naka, Andheri (E), Mumbai, India - 400 059

📍 **Factory Address :** Survey No. 85/8, 85/9, 85/10, 68/1, 70/14, Khattalwada, Manekpur Road, Tal - Umbergaon, Dist-Valsad, Station-Sanjan, Gujarat - 396120

Warranty

This product is warranted to be free from defects in materials when used and maintained as directed. Material installation as per viva guidelines detailed guidelines and warranty conditions are mentioned in warranty agreement.

In case of defects our doubts, please feel free to revert us at:

qc@vivaacp.com

qc.factory@vivaacp.com



 info@vivaacp.com

 www.vivaacp.com

 1800 313 3770 (Toll Free)

 **Registered Office :** A-601, Times Square, Marol Naka, Andheri (E), Mumbai, India - 400 059

 **Factory Address :** Survey No. 85/8, 85/9, 85/10, 68/1, 70/14, Khattalwada, Manekpur Road, Tal - Umbergaon, Dist-Valsad, Station-Sanjan, Gujarat - 396120